

Dual Cure 180

High-Gloss
DTM Polyaspartic



U.S. Patents:
6,833,424 & 7,169,876

Description:

DualCure 180 is a unique, high build, high gloss direct to metal finish. Engineered to provide excellent exterior durability, flexibility and superior adhesion to blasted, primed or e-coated surfaces. This fast curing coating system is designed to provide superior performance and enhanced productivity without the need for heat for drying. DualCure 180 offers excellent long term protection in moderate environments. Resistant to fresh water, salt water, fumes and spills of mild chemicals. Abrasion and moisture resistant, DualCure finishes are our longest lasting most durable topcoats. DualCure 180 is recommended for commercial and industrial use on machinery, trailers, containers, implements, structures and vehicles. Great for applications where excellent color and gloss retention are expected, while providing a smooth finish.

Advantages:

- Excellent Color and Gloss Retention
- High Gloss Finish
- Increased Productivity
- Flexibility
- 1-Hr Dry Time
- No Heat Cure
- Good Corrosion Resistance
- High Abrasion Resistance

Uses:

- Heavy-Duty Machinery
- Trailers
- Containers
- Implements
- Exterior Steel
- Vehicles
- Marine

Surface Preparation:

New or Unfinished Surfaces:

Ferrous Metal: Possibly suitable **“Direct to Metal”** application **to abrasive blasted surface.**

“Commercial Blast Cleaning” (SSPC-SP6) is recommended as the minimum for blast cleaning. Proper blast media and blasting equipment shall be used to produce a minimum profile depth of 1.5 mils minimum. Do not reuse abrasive media. Remove blasting dust and grit from surfaces before painting. Blasted surfaces should be coated within 8 hours after blasting or before rusting or other contamination of the surface occurs.

If blasting is not possible, a primer is required along with chemical cleaning or pretreatment.

Suitable Primers: SteelKote 825, SteelKote 850, SteelKote 900, DualCure 306

Galvanized Metal: Clean all contamination by scrubbing with a cleaning soap solution. Abrasive Blast and apply DualCure 306 Primer.

Aluminum or Stainless Steel: For best performance, application to abrasive blasted surface is recommended or etch with a phosphoric acid pretreatment solution is recommended for maximum adhesion. Clean all contamination by scrubbing with a cleaning soap solution. Prime with Steelkote 950 Multi Surface Epoxy Primer.

Mixing Instructions:

Thoroughly mix product, preferably using a mechanical mixing device. The temperature of the mixed product should be at least 45°F during application. Mix 3 Parts of DualCure 180 Part A with 2 Parts of ACT-953 Activator.

Material Properties

Gloss Level	95 units at 60°
Density	9.96 lbs/gal mixed
Volume Solids	73% (mixed)
VOC	2.13lbs./gal (255 grams/ltr) mixed
Dry Film Thickness	2.0 - 4.0 mils
Colors Available	Full ColorLinks Spectrum
Pot Life (68°F/20°C)	40 minutes mixed
Theoretical Coverage	585 ft ² / gal @ 2.0 mils dry film thickness
Practical Coverage	As a guideline for airless spraying on large dimensions: 70% of theoretical coverage. For small dimensions: 50%

Application Instructions

Spray Method	Airless	Air Assisted Airless	Air Spray / HVLP
Thinner	N/A	N/A	MAK
Quantity	N/A	N/A	0-10%
Nozzle or Tip Size	0.011-0.013	0.011-0.013	1.0-1.5
Fluid Pressure	2000 - 3000 PSI	1000 - 1500 PSI	8-10 PSI
Air Pressure	N/A	50 PSI	45 PSI
Dry Film Thickness	2.0 - 4.0 Mils	2.0 - 4.0 Mils	2.0 - 4.0 Mils

Performance Characteristics

Accelerated Weathering:
 ISO 11507 / ASTM G154 2000 hours
 ISO 2813 / ASTM D523 gloss retention @ 60° > 80%

Florida Black Box Exposure N/A

Impact (Direct & Indirect) 100 in lbs
 ASTM D-2794

Chemical Resistance 50 Double MEK Rubs

Flexibility: Cylindrical Mandrel
 ISO 1519 / ASTM D522 Passes 1/4"

Abrasion Resistance: Taber CS-17 / 1kg 400
 ASTM D4060 cycles: 130 mg loss

Salt Spray Direct to Blasted Metal
 ASTM B-117 Pass 250 hours

Dry Times: 70°F @ 3-5 mils DFT

To Touch: 30 Minutes

To Handle: 1-hour

To Re-Coat: 1-hour minimum / 12 hours
 maximum @ 2.5 mils dry

Force Cure: Do not force cure, heat will not
 help product cure faster

Health & Environmental:

In accordance with OSHA regulations on hazardous materials, harmful and irritating if in contact with skin, eyes and by inhalation. Observe safety information from SDS sheets. Always wear proper protective suits, gloves and eye protection. In case of eye contact, immediately wash with large amounts of water and contact a medical expert. If spraying, always wear proper NIOSH approved respirators. Fresh air fed respirators are preferred. Do not eat, drink or smoke during application. Discharge, treatment or disposal is subject to federal, state, commonwealth, provincial and local laws. Since empty containers retain product residue, follow label warnings even after container is emptied. Residual vapors may explode on ignition; do not cut, drill, grind or weld on or near this container.

Clean Up Instructions:

Cleaning tools: Clean immediately after application using MEK.

Warranty / Disclaimer:

The technical data and other printed information furnished are true and accurate to the best of our knowledge. The products are warranted pursuant to acceptance of limited warranty. A copy of which can be obtained from Baril Coatings, which is the exclusive warranty with respect to the sale of this product. The modification of any component or uses not outlined in this bulletin nullifies the warranty unless advance written confirmation is obtained from Baril Coatings. No other warranties expressed or implied shall apply. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, shall be to supply replacement materials as set forth in the limited warranty.