

# FleetSpec™ 1210

HS Urethane Medium Speed



## Description:

FleetSpec™ 1210 is a High Solids High Gloss Urethane Topcoat. It is an ideal option for OEM applications, fleet refinish and many other similar industry applications. FleetSpec™ 1210 provides for high quality, rapid turn around and long lasting performance. 1210 offers excellent durability against harsh chemicals, superior chip resistance and UV ray protection.

## Advantages:

- Long-term color and gloss retention
- Application of multiple back to back coats without runs
- Excellent chemical resistance
- Superior flexibility
- Long working times and user-friendly application

## Common Applications:

- OEM
- Industrial Refinishing
- Construction Equipment
- Truck and Trailer Refinish

## System Components:

- 1210 Series Color
- ACT75 for National Rule
- ACTZ65 for ≤ 2.8 VOC
- S660, S670, S690 reducers (Nat'l)
- SZ Series reducers (<2.8 VOC).
- SLV Series reducers for 3.5 VOC

## Surface Preparation:

Clean surface with solvent or water based cleaner. Sand entire surface with 320 grit, or 220 grit sandpaper and blow off all dust and clean surface with both solvent based cleaner and water based cleaner. Lightly wipe down with tack rag.

## Coating Compatibility: FleetSpec 1210 may be applied over any of the following

- 850 MS Epoxy Primer
- 825 FD Epoxy Primer
- 305 and 306 Zinc Rich Urethane Primer
- 900 High Build Urethane Primer
- 750 ISO-Free 2k High Build DTM Primer

Existing Coatings: 1210 may be applied over most aged and cured coatings in good condition. Testing for lifting, bubbling, and adhesion is recommended to assure compatibility with unknown coatings.

## Color:

FleetSpec™ 1210 utilizes the Baril ColorLinks™ intermix platform. ColorLinks™ offers unlimited color availability with a database comprising thousands of existing fleet color formulations. Available in solid-color, metallic and pearl finishes, ColorLinks™ lab technicians can also custom match colors as required.

Color is available as a pre-mixed factory pack or in a toner bank platform for on-site color matching.

## Material Properties

Gloss Level (60° angle)	95
Weight Solids	62% (average)
Volume Solids	55% (average)
VOC	1.35-3.55 depending on activator used
Pot Life	1 Hour @ 70°F
Flash Time @ 70°F	10-15 minutes depending on reducer used.
Dry Times	Tack Free: 15 Minutes Dry To Touch & Handle: 4 Hours Through Cure: 12 Hours



### Gun Setups:

Airless and Air Assist Airless – 1004-1006 or 1104-1106 nozzle. (Not Recommended)

Pressure Pot – 1.0-1.1 tip and needle

Gravity Feed: 1.3 mm – 1.5 mm

Siphon Feed: 1.3 mm – 1.5 mm

### Air Pressures:

- Airless and Air Assist Airless, See particular equipment standards. (Not Recommended)
- Pressure Pot Liquid Back Pressure 2 qt – 8-12 lbs., 3 gl. – 12-18 lbs., 5 gl. – 18-25 lbs.
- Pressure Pot Gun Pressure 24-35 lbs.
- Gravity Feed 24 – 28 psi
- HVLP at cap 8 – 10 psi

### Application:

Apply two medium wet coats allowing 10-25 minutes flash time between coats. Mill build should be 1.3-1.8 mills per coat. Two coats are recommended to get full protection against environment and UV resistance. One coat with a cross coat is admissible if two dry mills can be achieved.

### Safety:

Refer to Safety Data Sheet (SDS) for complete safety instructions. The Painters Technical Information Sheet listed has been compiled in good faith for your convenience and guidance.

### Application Details

Mix Ratios:	3 Parts 1210 Series Color to 1 Part selected Activator and 1 Part selected Reducer
Application Environment:	Do not apply if the surface temperature of the object to be painted is below 50°F (10°C) or above 100°F (37.8°C)
Application Equipment	Contact Your Baril Coatings Representative for specific application equipment recommendations.
Shelf Life	2 years from date of manufacture. Store in a well-ventilated area. Storage conditions should be between 35° F (2° C) and 120° F (48° C). Shake up or Stir Up completely before Activation and Application.
Cleaning Instructions	Use required cleaner depending on Local Area Regulations. (Check local regulations)

### Chemical Resistance: ASTM D 1308

Chemical	Rating 10:best, 1:worst
10% Sodium Hydroxide	10
Diesel Fuel	10
10% Ammonia	10
100% Ethanol	10
10% Sulfuric Acid	10
10% Phosphoric Acid	10
MEK (Methyl Ethyl Ketone)	10
Gasoline	10
Skydrol	10
DOT 3 Brake Fluid	10

### Warranty / Disclaimer:

The technical data and other printed information furnished are true and accurate to the best of our knowledge. The products are warranted pursuant to acceptance of limited warranty. A copy of which can be obtained from Baril Coatings, which is the exclusive warranty with respect to the sale of this product. The modification of any component or uses not outlined in this bulletin nullifies the warranty unless advance written confirmation is obtained from Baril Coatings. No other warranties expressed or implied shall apply. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, shall be to supply replacement materials as set forth in the limited warranty.

